



Zacatecas Project
Pánuco Target
Drill Hole Results
Holes 1 to 24

DDH - PA-09-01

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0901-35	53.01	53.21	0.2	0.080	751.0	116	32	343	294
PA0901-40	55.41	55.6	0.19	0.005	10.0	92	39	27	77
PA0901-45	57.10	57.3	0.2	0.521	127.0	34	11	188	32
PA0901-103	148.60	149.47	0.87	0.007	6.1	57	5	30	67
PA0901-104	149.47	149.87	0.4	0.124	17.8	185	299	142	1035
PA0901-105	149.87	150.15	0.28	0.020	8.1	36	42	24	86
PA0901-106	150.15	150.56	0.41	0.007	4.7	56	10	24	107
PA0901-107	150.56	150.82	0.26	0.032	11.2	59	10	36	70
PA0901-108	150.82	151.38	0.56	0.023	3.5	18	7	29	20
PA0901-109	151.38	152.25	0.87	0.036	19.7	178	157	52	148
PA0901-110	152.25	153.05	0.8	0.033	7.1	108	27	58	75
PA0901-136	173.98	174.46	0.48	0.036	3.4	27	20	15	84
PA0901-137	174.46	174.92	0.46	0.542	1710.0	301	1.64%	2080	8.54%
PA0901-138	174.92	175.34	0.42	0.187	19.6	44	48	96	225
PA0901-139	175.34	175.76	0.42	0.127	281.0	209	438	265	807
PA0901-140	175.76	176.25	0.49	0.065	26.8	59	107	74	563
PA0901-141	176.25	177.02	0.77	0.044	11.5	241	213	39	181

DDH - PA-09-02

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0902-128	223.46	224.04	0.58	0.037	4.6	45	8	42	50
PA0902-129	224.04	224.29	0.25	0.105	15.7	249	165	88	601
PA0902-130	224.29	224.69	0.4	0.041	10.2	313	62	34	282
PA0902-131	224.69	225.12	0.43	0.090	3.7	65	4	60	49
PA0902-132	225.12	225.71	0.59	0.021	3.4	66	4	33	63
PA0902-133	225.71	225.95	0.24	0.067	3.9	16	4	30	31
PA0902-134	225.95	226.22	0.27	0.267	16.8	27	5	81	25
PA0902-135	226.22	226.57	0.35	0.450	8.3	17	6	97	19
PA0902-136	226.57	227.27	0.7	0.097	12.5	47	6	55	31
PA0902-137	227.27	227.80	0.53	0.071	3.9	15	5	27	30
PA0902-138	227.80	228.13	0.33	0.589	6.3	22	8	174	43
PA0902-139	228.13	228.60	0.47	0.084	3.2	15	3	35	167
PA0902-140	228.60	229.58	0.98	0.025	2.4	53	2	22	72
PA0902-141	229.58	230.10	0.52						

DDH - PA-09-03

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0903-102	162.02	163.15	1.13						
PA0903-103	163.15	163.57	0.42	0.172	129.0	125	345	224	251
PA0903-104	163.57	164.15	0.58	0.068	58.6	192	410	87	878
PA0903-105	164.15	164.40	0.25	0.027	32.9	42	12	53	413
PA0903-106	164.40	164.92	0.52	0.048	52.4	80	164	79	791
PA0903-107	164.92	165.85	0.93	0.041	15.3	91	5	47	263
PA0903-108	165.85	166.21	0.36	0.018	5.1	31	3	27	146
PA0903-109	166.21	166.65	0.44	0.037	17.8	60	12	59	135
PA0903-110	166.65	167.02	0.37	0.010	2.3	9	2	17	23
PA0903-111	167.02	167.23	0.21	0.199	63.0	67	10	94	129
PA0903-112	167.23	167.80	0.57						

DDH - PA-09-04

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0904-71	115.25	115.74	0.49	0.010	1.2	90	<2	19	97
PA0904-72	115.74	115.95	0.21	0.135	21.8	83	30	109	398
PA0904-73	115.95	116.45	0.50	0.276	538.0	321	387	347	1025
PA0904-74	116.45	116.85	0.40	0.219	79.0	27	90	162	59
PA0904-75	116.85	117.05	0.20	0.134	533.0	96	636	578	116
PA0904-76	117.05	117.58	0.53	0.040	6.7	72	<2	159	42
PA0904-80	122.44	122.64	0.20						

DDH - PA-09-05

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0905-36	57.12	57.69	0.57	0.005	<0.5	84	<2	<5	44
PA0905-46	70.22	70.91	0.69	0.008	2.8	47	4	36	66
PA0905-47	70.91	71.25	0.34	<0.005	1.0	71	<2	<5	52
PA0905-48	71.25	71.53	0.28	<0.005	<0.5	70	<2	<5	51

DDH - PA-09-06

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0906-83	142.01	142.29	0.28	0.008	3.6	46	5	41	64
PA0906-84	142.29	142.66	0.37	0.020	8.2	263	9	70	98
PA0906-85	142.66	143.14	0.48	0.014	4.4	174	12	32	139
PA0906-86	143.14	144.00	0.86	0.006	1.0	45	7	22	87
PA0906-87	144.00	144.30	0.30	0.009	1.0	134	10	19	89
PA0906-94	150.23	150.83	0.60	0.023	16.2	279	2	85	42
PA0906-95	150.83	151.43	0.60	0.036	60.2	329	6	74	53
PA0906-96	151.43	151.90	0.47	0.012	11.4	248	5	76	31
PA0906-97	151.90	152.27	0.37	0.200	23.1	4080	13	247	48
PA0906-98	152.27	152.53	0.26	0.489	278.0	>10000	85	599	92
PA0906-99	152.53	153.08	0.55	0.362	148.0	6740	171	322	648
PA0906-100	153.08	153.40	0.32	0.029	12.3	235	17	106	80
PA0906-101	153.40	153.90	0.50	0.012	7.9	357	24	95	160
PA0906-105	157.40	157.90	0.50	0.291	21.2	7170	112	195	623
PA0906-110	165.67	165.84	0.17	<0.005	0.5	107	2	26	44
PA0906-112	167.80	168.05	0.25	0.177	4.5	6060	2	112	244
PA0906-117	172.53	172.90	0.37	0.036	3.9	1540	<2	158	30
PA0906-118	172.90	173.33	0.43	0.032	3.8	877	5	106	14
PA0906-119	173.33	173.83	0.50	0.211	12.1	6350	7	173	15
PA0906-120	173.83	174.20	0.37	0.598	29.6	>10000	4	364	16
PA0906-121	174.20	174.58	0.38	0.380	8.3	5980	2	164	7
PA0906-122	174.58	175.23	0.65	0.008	1.3	234	4	40	29

DDH - PA-09-07

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0907-61	110.00	110.94	0.94	0.050	13.7	29	29	55	81
PA0907-95	164.30	164.84	0.54	<0.005	2.4	90	5	29	69
PA0907-96	164.84	165.22	0.38	0.024	8.9	30	6	49	28
PA0907-97	165.22	165.64	0.42	0.138	9.4	11	5	101	16
PA0907-98	165.64	165.95	0.31	0.104	71.7	31	28	115	392
PA0907-99	165.95	166.47	0.52	0.014	7.2	64	9	45	93
PA0907-127	204.10	204.30	0.20	0.050	4.1	22	4	50	44
PA0907-128	204.30	204.73	0.43	1.105	91.4	39	7	448	76
PA0907-129	204.73	205.14	0.41	1.440	34.1	39	9	676	1945
PA0907-130	205.14	205.80	0.66	0.071	13.3	52	3	60	50
PA0907-137	213.73	214.18	0.45	0.128	73.1	27	15	55	34
PA0907-158	251.30	251.80	0.50	<0.005	1.9	57	4	32	45
PA0907-159	251.80	252.52	0.72	<0.005	1.4	62	2	36	55
PA0907-160	252.52	253.33	0.81	<0.005	1.8	70	6	34	75
PA0907-161	253.33	253.85	0.52	0.008	3.6	55	7	29	29
PA0907-162	253.85	254.36	0.51	0.032	41.9	19	16	41	47
PA0907-163	254.36	254.78	0.42	0.146	770.0	129	387	410	443
PA0907-164	254.78	255.18	0.40	0.146	236.0	69	94	176	136
PA0907-165	255.18	255.58	0.40	0.218	2190.0	580	1195	1175	1610
PA0907-166	255.58	256.07	0.49	0.153	2870.0	475	753	1430	1550
PA0907-167	256.07	256.45	0.38	0.033	61.2	89	29	66	105
PA0907-168	256.45	256.85	0.40	0.039	60.2	62	28	65	99
PA0907-169	256.85	257.30	0.45	0.088	9.4	51	<2	80	32
PA0907-170	257.30	257.76	0.46	0.040	6.2	59	<2	32	40
PA0907-171	257.76	258.15	0.39	0.117	5.3	10	3	75	80
PA0907-187	285.45	285.65	0.20	0.006	20.5	83	10	15	193
PA0907-199	307.05	307.49	0.44	0.133	33.0	5	6	93	13

DDH - PA-09-08									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0908-75	119.17	119.36	0.19	0.026	5.4	27	15	322	30
PA0908-88	130.43	131.17	0.74	0.011	1.3	3	6	14	46
PA0908-89	131.17	131.34	0.17	0.067	6.3	75	4	103	95
PA0908-90	131.34	131.67	0.33	0.007	3.2	22	6	78	156
PA0908-91	131.67	132.93	1.26	0.009	1.5	1	4	22	145
PA0908-92	132.93	133.82	0.89	0.008	1.3	<1	6	41	107
PA0908-93	133.82	134.83	1.01	0.133	1.7	2	6	88	49
PA0908-94	134.83	135.59	0.76	0.019	2.0	<1	8	35	48
PA0908-95	135.59	136.14	0.55	0.074	5.2	3	9	51	40
PA0908-96	136.14	136.88	0.74	0.119	18.5	16	14	285	137
PA0908-97	136.88	137.41	0.53	0.213	13.4	16	4	118	69
PA0908-98	137.41	137.86	0.45	0.017	6.0	64	2	62	240
PA0908-99	137.86	138.19	0.33	0.028	3.3	8	2	67	86
PA0908-100	138.19	138.43	0.24	0.133	12.7	69	5	205	70
PA0908-101	138.43	138.70	0.27	0.052	3.8	10	2	73	104
PA0908-102	138.70	139.54	0.84	0.025	4.2	51	2	106	88
PA0908-103	139.54	139.85	0.31	0.012	2.6	60	<2	70	63
PA0908-104	139.85	140.62	0.77	0.019	2.7	46	4	117	19
PA0908-105	140.62	141.62	1.00	0.084	11.5	39	11	123	41
PA0908-108	143.62	144.62	1.00	0.030	8.7	43	24	150	61
PA0908-110	145.53	146.33	0.80	<0.005	<0.5	70	<2	54	77
PA0908-113	148.20	149.22	1.02	<0.005	1.9	50	<2	55	42
PA0908-114	149.22	150.29	1.07	0.006	3.3	58	2	22	54
PA0908-116	151.29	151.67	0.38	0.013	2.6	53	<2	28	20
PA0908-121	157.49	157.68	0.19	0.038	6.0	120	<2	40	41
PA0908-123	158.11	158.32	0.21	<0.005	1.8	71	<2	20	28
PA0908-129	163.10	163.47	0.37	0.022	1.8	52	<2	57	16
PA0908-134	168.03	168.28	0.25	0.026	1.0	66	<2	32	21
PA0908-134-BIS	168.28	169.40	1.12	0.007	1.8	88	<2	43	44
PA0908-135	169.40	169.63	0.23	0.226	3.4	44	4	166	22
PA0908-136	169.63	169.96	0.33	0.019	2.2	9	4	60	36
PA0908-137	169.96	171.00	1.04	0.012	3.4	81	3	73	18
PA0908-138	171.00	172.00	1.00	0.017	2.9	52	<2	51	25
PA0908-139	172.00	173.00	1.00	0.030	2.2	27	12	81	34

DDH - PA-09-08 (continued)									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0908-140	173.00	173.98	0.98	0.012	2.1	58	<2	75	30
PA0908-141	173.98	174.34	0.36	0.060	4.6	37	4	134	24
PA0908-142	174.34	175.11	0.77	0.005	2.1	77	2	54	33
PA0908-145	178.54	178.82	0.28	0.010	1.7	22	<2	39	52
PA0908-146	178.82	179.81	0.99	0.032	2.9	41	<2	82	31
PA0908-147	179.81	180.90	1.09	0.018	3.6	59	<2	78	86
PA0908-148	180.90	181.07	0.17	0.051	7.2	39	5	75	35
PA0908-149	181.07	181.40	0.33	0.139	10.9	68	8	194	30
PA0908-150	181.40	181.65	0.25	0.143	6.1	13	3	147	19
PA0908-151	181.65	182.26	0.61	0.288	9.2	25	6	328	17
PA0908-152	182.26	183.43	1.17	0.061	11.1	58	<2	109	35
PA0908-153	183.43	183.73	0.30	0.265	6.3	45	5	284	31
PA0908-154	183.73	185.00	1.27	0.018	2.6	54	<2	80	71
PA0908-155	185.00	185.69	0.69	0.011	1.9	65	<2	85	64
PA0908-156	185.69	186.39	0.70	0.023	2.5	54	<2	76	59
PA0908-157	186.39	186.68	0.29	0.139	3.6	33	2	157	30
PA0908-158	186.68	187.50	0.82	0.013	2.9	69	<2	47	21
PA0908-159	187.50	188.07	0.57	<0.005	0.9	81	2	27	59
PA0908-160	188.07	188.41	0.34	<0.005	<0.5	65	<2	24	67
PA0908-161	188.41	188.84	0.43	<0.005	0.8	63	3	61	95
PA0908-178	210.57	211.35	0.78	<0.005	0.9	72	<2	39	87
PA0908-179	211.35	212.14	0.79	<0.005	1.3	37	3	37	43
PA0908-180	212.14	212.98	0.84	0.024	5.2	77	4	39	75
PA0908-181	212.98	213.23	0.25	0.019	2.4	18	2	19	9
PA0908-182	213.23	213.58	0.35	0.014	3.3	49	<2	36	67
PA0908-183	213.58	214.17	0.59	0.008	1.5	52	2	29	55
PA0908-184	214.17	214.86	0.69	<0.005	<0.5	59	2	50	91
PA0908-185	214.86	215.21	0.35	<0.005	1.3	100	<2	24	54
PA0908-186	215.21	215.51	0.30	<0.005	<0.5	45	<2	18	62
PA0908-187	215.51	215.96	0.45	<0.005	0.5	74	<2	18	80
PA0908-188	215.96	216.47	0.51	<0.005	0.6	35	<2	31	67
PA0908-190	217.72	218.73	1.01	<0.005	0.6	62	<2	41	56
PA0908-191	218.73	219.18	0.45	<0.005	1.5	66	<2	49	105
PA0908-192	219.18	219.57	0.39	<0.005	1.9	58	4	35	83
PA0908-194	220.88	221.40	0.52	0.007	3.2	61	4	34	50

DDH - PA-09-08 (continued)

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0908-195	221.40	221.70	0.30	0.014	2.0	20	<2	42	30
PA0908-196	221.70	222.59	0.89	<0.005	0.9	73	3	43	74
PA0908-199	223.78	224.55	0.77	<0.005	0.7	87	<2	22	42
PA0908-200	224.55	224.76	0.21	<0.005	0.5	42	2	24	29
PA0908-201	224.76	225.97	1.21	<0.005	<0.5	77	<2	20	47
PA0908-204	228.00	229.00	1.00	<0.005	<0.5	67	<2	20	39
PA0908-205	229.00	229.96	0.96	<0.005	<0.5	76	<2	32	63
PA0908-207	231.40	232.70	1.30	<0.005	<0.5	67	<2	24	48
PA0908-207-BIS	232.70	234.00	1.30	<0.005	<0.5	56	<2	25	35
PA0908-208	234.00	236.00	2.00	<0.005	0.6	79	<2	36	47
PA0908-209	236.00	237.44	1.44	<0.005	<0.5	34	<2	25	33
PA0908-213	240.42	241.50	1.08	<0.005	<0.5	21	6	8	103

DDH - PA-09-09

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0909	124.61	125.19	0.58	<0.5	42.0	36	3	517	56

DDH - PA-09-10

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0910-56	101.37	102.16	0.79	0.006	<0.5	51	<2	12	81
PA0910-57	102.16	102.97	0.81	<0.005	<0.5	51	5	8	80
PA0910-58	102.97	103.72	0.75	<0.005	<0.5	41	2	14	93
PA0910-59	103.72	104.36	0.64	<0.005	<0.5	92	<2	19	81
PA0910-60	104.36	104.97	0.61	<0.005	<0.5	61	3	14	87
PA0910-110	204.00	204.17	0.17	0.010	<0.5	68	20	20	84
PA0910-125	226.34	226.97	0.63	0.011	2.0	57	3	22	59
PA0910-126	226.97	227.45	0.48	0.215	3.3	23	5	121	35
PA0910-127	227.45	227.72	0.27	0.170	3.5	22	5	93	16
PA0910-128	227.72	228.12	0.4	0.239	5.1	29	6	165	37
PA0910-129	228.12	228.73	0.61	0.049	3.3	38	5	49	48
PA0910-146	258.30	259.29	0.99	0.007	<0.5	47	8	15	113
PA0910-147	259.29	260.33	1.04	0.014	2.1	53	11	21	126
PA0910-156	274.05	274.69	0.64	<0.005	0.6	34	2	18	65

DDH - PA-09-10 (continued)									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0910-157	274.69	275.13	0.44	0.022	2.6	94	<2	41	9
PA0910-158	275.13	276.18	1.05	<0.005	1.1	65	<2	23	70
PA0910-159	276.18	277.27	1.09	<0.005	<0.5	65	<2	24	74
PA0910-160	277.27	277.70	0.43	<0.005	<0.5	57	<2	17	67
PA0910-161	277.70	278.13	0.43	0.006	1.1	64	2	28	61
PA0910-162	278.13	278.93	0.8	0.008	<0.5	82	2	29	104
PA0910-163	278.93	279.19	0.26	<0.005	<0.5	36	<2	13	37
PA0910-164	279.19	279.75	0.56	<0.005	1.0	62	2	33	51
PA0910-165	279.75	280.09	0.34	<0.005	1.3	32	<2	21	21
PA0910-166	280.09	280.54	0.45	0.005	1.4	69	4	30	44
PA0910-167	280.54	280.85	0.31	0.006	0.8	20	<2	23	39
PA0910-168	280.85	281.40	0.55	<0.005	<0.5	49	<2	33	43
PA0910-169	281.40	282.15	0.75	<0.005	1.4	69	<2	27	51
PA0910-170	282.15	283.09	0.94	<0.005	0.8	70	<2	23	58
PA0910-171	283.09	284.25	1.16	<0.005	0.9	68	<2	25	58
PA0910-172	284.25	284.72	0.47	0.012	3.3	62	<2	44	54
PA0910-173	284.72	285.33	0.61	0.714	14.6	56	3	104	53
PA0910-174	285.33	285.75	0.42	0.010	2.5	68	6	20	54
PA0910-175	285.75	286.29	0.54	0.009	2.6	80	<2	23	82
PA0910-187	302.87	303.59	0.72	0.014	3.2	205	92	33	82
PA0910-188	303.59	303.93	0.34	0.050	29.1	56	18	71	53
PA0910-189	303.93	304.30	0.37	0.005	1.1	51	4	26	43
PA0910-194	311.89	312.78	0.89	<0.005	2.2	79	4	30	70
PA0910-195	312.78	313.83	1.05	0.042	4.0	62	5	55	41
PA0910-196	313.83	314.16	0.33	0.639	40.3	50	13	236	141
PA0910-197	314.16	314.63	0.47	1.045	233.0	43	33	456	186
PA0910-198	314.63	315.75	1.12	0.005	1.3	67	7	23	50
PA0910-202	319.24	319.47	0.23	0.011	0.7	37	11	20	53

DDH - PA-09-11

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0911-32	51.26	52.19	0.93	<0.005	1.4	56	16	51	66
PA0911-33	52.19	53.1	0.91	0.041	1.9	43	9	32	43
PA0911-34	53.10	53.76	0.66	0.095	8.1	17	13	54	34
PA0911-35	53.76	54.20	0.44	0.051	3.9	17	8	23	33
PA0911-36	54.20	54.93	0.73	0.007	1.7	53	6	27	38
PA0911-42	64.30	64.96	0.66	0.005	<0.5	44	5	19	55
PA0911-52	80.15	80.68	0.53	<0.005	<0.5	61	3	<5	56
PA0911-63	96.33	97.00	0.67	<0.005	<0.5	14	10	21	31
PA0911-77	121.12	121.50	0.38	0.012	2.2	25	6	28	78
PA0911-94	149.06	149.62	0.56	<0.005	1.3	60	4	48	77
PA0911-95	149.62	149.95	0.33	0.142	48.6	16	220	248	642
PA0911-96	149.95	150.29	0.34	0.228	18.6	27	142	201	382
PA0911-97	150.29	150.87	0.58	0.187	8.7	46	13	299	67
PA0911-98	150.87	151.50	0.63	0.104	9.8	35	8	182	56
PA0911-99	151.50	152.12	0.62	0.052	24.4	42	6	131	62
PA0911-100	152.12	152.94	0.82	0.059	7.7	47	4	136	53
PA0911-101	152.94	153.46	0.52	0.020	14.7	48	9	89	65
PA0911-102	153.46	153.92	0.46	0.031	96.9	48	9	190	59
PA0911-103	153.92	154.32	0.40	0.099	10.3	15	101	300	136
PA0911-104	154.32	155.33	1.01	0.025	3.2	63	<2	59	59
PA0911-105	155.33	156.00	0.67	<0.005	<0.5	82	22	31	55

DDH - PA-09-12									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0912-43	78.72	79.10	0.38	0.005	<0.5	20	5	7	118
PA0912-44	79.10	79.33	0.23	<0.005	<0.5	8	<2	15	86
PA0912-45	79.33	80.20	0.87	0.005	3.0	72	7	45	69
PA0912-46	80.20	80.55	0.35	0.266	11.5	6	54	403	21
PA0912-47	80.55	81.07	0.52	0.144	5.3	4	14	155	27
PA0912-48	81.07	81.40	0.33	0.044	1.8	10	5	41	32
PA0912-53	85.58	86.30	0.72	0.010	2.3	99	<2	29	19
PA0912-54	86.30	86.86	0.56	0.005	0.6	14	<2	22	34
PA0912-55	86.86	87.16	0.30	0.170	1.6	8	2	89	25
PA0912-56	87.16	87.55	0.39	0.012	1.1	23	3	26	98
PA0912-57	87.55	88.00	0.45	0.011	1.3	55	4	16	474
PA0912-81	131.69	131.95	0.26	0.011	2.3	39	5	17	41
PA0912-84	133.52	134.22	0.70	0.006	<0.5	30	<2	219	30
PA0912-85	134.22	135.14	0.92	<0.005	0.6	35	<2	63	28
PA0912-86	135.14	136.00	0.86	<0.005	<0.5	55	<2	48	40
PA0912-108	163.90	164.92	1.02	0.007	0.9	73	<2	6	45
PA0912-132	197.88	198.45	0.57	<0.005	<0.5	46	5	16	139
PA0912-194	305.68	306.00	0.32	0.011	0.8	4	4	15	29
PA0912-224	362.47	362.79	0.32	<0.005	<0.5	18	4	<5	93
PA0912-226	363.54	364.15	0.61	<0.005	<0.5	19	4	5	93
PA0912-233	372.12	372.42	0.30	<0.005	<0.5	30	3	<5	62
PA0912-249	394.47	394.80	0.33	0.036	5.8	103	10	97	149
PA0912-250	394.80	395.07	0.27	0.023	12.6	37	<2	53	76
PA0912-251	395.07	395.50	0.43	0.065	93.6	18	11	71	27
PA0912-252	395.50	396.18	0.68	0.015	7.0	34	<2	33	75
PA0912-253	396.18	396.59	0.41	0.364	363.0	54	25	385	47
PA0912-254	396.59	397.06	0.47	0.014	2.1	41	5	23	71
PA0912-258	401.57	402.38	0.81	<0.005	<0.5	10	2	8	95
PA0912-258 BIS	402.38	402.79	0.41						
PA0912-259	402.79	403.17	0.38	<0.005	<0.5	7	3	6	61
PA0912-261	404.60	404.94	0.34	0.005	0.8	23	4	9	67
PA0912-265	409.09	409.91	0.82	0.005	0.7	26	4	7	72
PA0912-278	426.05	427.00	0.95	<0.005	<0.5	68	<2	10	42
PA0912-279	427.00	428.00	1.00	<0.005	<0.5	66	<2	8	63
PA0912-280	428.00	428.96	0.96	<0.005	<0.5	82	<2	11	63
PA0912-281	428.96	429.52	0.56	<0.005	<0.5	12	5	8	20

DDH - PA-09-12 (continued)

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0912-282	429.52	429.90	0.38	<0.005	<0.5	2	2	<5	36
PA0912-295	451.00	451.63	0.63	<0.005	<0.5	59	2	15	329
PA0912-296	451.63	451.84	0.21	<0.005	<0.5	20	<2	5	96
PA0912-297	451.84	452.53	0.69	0.010	0.7	57	18	7	197
PA0912-298	452.53	453.00	0.47	0.019	0.9	23	13	<5	25
PA0912-299	453.00	453.25	0.25	0.012	1.0	37	12	<5	68

DDH - PA-09-13

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0913-131	230.85	232.00	1.15	0.013	3.7	144	22	52	250
PA0913-133	232.70	233.53	0.83	0.014	2.3	130	40	8	184
PA0913-134	233.53	234.00	0.47	0.014	3.1	131	59	16	126
PA0913-135	234.00	235.00	1.00	0.014	2.6	70	39	16	128
PA0913-136	235.00	236.00	1.00	0.011	1.9	60	31	22	146
PA0913-139	237.52	238.46	0.94	0.007	0.9	21	11	18	100
PA0913-140	238.46	238.87	0.41	<0.005	<0.5	75	<2	23	63
PA0913-141	238.87	239.40	0.53	<0.005	<0.5	74	10	18	57
PA0913-142	239.40	239.75	0.35	0.009	2.1	40	4	33	40
PA0913-143	239.75	240.21	0.46	<0.005	1.4	56	5	6	80
PA0913-144	240.21	241.13	0.92	<0.005	0.9	75	6	13	47
PA0913-145	241.13	242.00	0.87	<0.005	0.9	24	6	11	19
PA0913-148	244.77	245.52	0.75	0.013	2.0	41	<2	18	30
PA0913-148-BIS	245.52	246.45	0.93	<0.005	1.7	54	4	19	68
PA0913-149	246.45	247.33	0.88	<0.005	1.4	53	5	16	80
PA0913-155	252.00	252.59	0.59	<0.005	<0.5	76	<2	19	29
PA0913-155-BIS	252.00	252.59	0.59	<0.005	0.7	11	<2	11	25
				<0.005	<0.5	48	2	12	50
				<0.005	4.8	36	3	29	28
				0.008	2.6	59	<2	15	47
				<0.005	0.9	66	<2	15	64
				<0.005	0.6	59	<2	14	55
				<0.005	0.6	73	<2	5	67
				<0.005	<0.5	81	4	6	66
				<0.005	<0.5	80	5	6	65

DDH - PA-09-13 (continued)									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0913-179	280.83	281.08	0.25	<0.005	<0.5	45	<2	6	48
PA0913-180	281.08	281.65	0.57	<0.005	0.5	88	12	8	48
PA0913-181	281.65	282.39	0.74	<0.005	0.6	79	<2	6	75
PA0913-182	282.39	282.93	0.54	<0.005	<0.5	63	<2	6	64
PA0913-183	282.93	283.45	0.52	<0.005	<0.5	66	<2	<5	60
PA0913-184	283.45	283.92	0.47	<0.005	<0.5	57	<2	5	53
PA0913-185	283.92	284.40	0.48	<0.005	<0.5	81	<2	15	91
PA0913-186	284.40	284.69	0.29	<0.005	<0.5	39	9	13	40
PA0913-187	284.69	284.99	0.30	<0.005	<0.5	42	17	18	36
PA0913-188	284.99	285.67	0.68	<0.005	<0.5	99	18	5	56
PA0913-206	311.73	312.43	0.70	<0.005	1.7	81	20	15	35
PA0913-207	312.43	312.89	0.46	<0.005	1.3	56	6	23	31
PA0913-208	312.89	313.41	0.52	<0.005	0.8	60	<2	13	56
PA0913-211	316.28	316.51	0.23	<0.005	<0.5	45	<2	15	31
PA0913-222	328.97	329.64	0.67	<0.005	0.5	47	3	14	55
PA0913-223	329.64	330.43	0.79	<0.005	0.8	24	3	12	33
PA0913-224	330.43	331.23	0.80	<0.005	1.1	34	<2	12	30
PA0913-235	349.12	350.00	0.88	0.115	24.0	62	4	117	193
PA0913-236	350.00	350.66	0.66	0.026	13.3	36	<2	92	39
PA0913-237	350.66	351.50	0.84	0.019	16.0	48	2	92	45
PA0913-238	351.50	352.00	0.50	0.020	4.2	30	4	43	168
PA0913-239	352.00	352.65	0.65	0.008	1.8	19	3	25	101
PA0913-240	352.65	353.45	0.80	0.011	2.6	16	2	34	78
PA0913-241	353.45	354.10	0.65	0.013	3.4	13	<2	30	69
PA0913-242	354.10	354.76	0.66	0.014	4.3	22	3	32	38

DDH - PA-09-14

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0914-24	44.36	44.76	0.40	0.006	<0.5	51	21	<5	95
PA0914-36	62.37	62.68	0.31	<0.005	<0.5	11	4	<5	40
PA0914-71	108.07	108.75	0.68	0.009	<0.5	18	9	8	42
PA0914-92	139.41	140.39	0.98	0.019	1.3	53	27	14	208
PA0914-93	140.39	141.13	0.74	<0.005	<0.5	12	6	5	98
PA0914-94	141.13	141.30	0.17	<0.005	0.5	89	6	14	88
PA0914-95	141.30	141.58	0.28	<0.005	0.6	57	4	18	52
PA0914-96	141.58	141.88	0.30	0.227	917.0	154	224	533	524
PA0914-97	141.88	142.23	0.35	0.042	3.5	46	5	30	46
PA0914-98	142.23	142.72	0.49	<0.005	2.0	62	4	41	56
PA0914-99	142.72	143.14	0.42	<0.005	0.6	54	<2	30	67
PA0914-100	143.14	143.55	0.41	0.021	344.0	94	13	219	78
PA0914-101	143.55	144.18	0.63	<0.005	1.4	54	<2	15	58
PA0914-102	144.18	145.16	0.98	<0.005	1.1	58	<2	11	63
PA0914-103	145.16	145.67	0.51	<0.005	1.0	66	5	8	52
PA0914-104	145.67	146.13	0.46	<0.005	1.3	59	2	6	55

DDH - PA-09-15

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-09-15-56	93.04	93.59	0.55	0.026	2.2	77	15	24	90
PA-09-15-57	93.59	93.9	0.31	0.068	0.7	99	5	23	63
PA-09-15-58	93.90	94.24	0.34	0.024	2.0	74	8	22	75
PA-09-15-60	95.71	96.16	0.45	<0.005	0.5	11	5	<5	190
PA-09-15-61	96.16	96.89	0.73	0.013	0.9	38	5	14	214
PA-09-15-62	96.98	98.00	1.02	<0.005	0.9	82	<2	21	103
PA-09-15-63	98.00	99.00	1.00	<0.005	1.0	65	4	21	109
PA-09-15-64	99.00	100.30	1.30	<0.005	1.7	73	<2	17	64
PA-09-15-65	100.30	100.85	0.55	0.016	2.3	52	2	18	43
PA-09-15-66	100.85	101.27	0.42	0.171	4.1	39	6	35	27
PA-09-15-67	101.27	101.97	0.70	0.037	64.8	68	4	55	67
PA-09-15-68	101.97	102.40	0.43	0.026	247.0	57	13	171	51
PA-09-15-69	102.40	103.08	0.68	0.037	5.4	75	2	113	53
PA-09-15-70	103.08	103.61	0.53	<0.005	13.6	53	2	78	42
PA-09-15-71	103.61	103.98	0.37	0.089	550.0	184	255	439	965
PA-09-15-72	103.98	104.25	0.27	0.041	156.0	145	40	126	82
PA-09-15-73	104.25	104.52	0.27	0.248	80.7	42	10	91	36
PA-09-15-74	104.52	105.42	0.90	<0.005	3.6	80	2	20	75

DDH - PA-09-16

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0916-87	132.13	133.14	1.01	<0.005	1.0	73	3	7	56
PA0916-88	133.14	133.38	0.24	<0.005	1.8	91	<2	10	62
PA0916-89	133.38	133.6	0.22	<0.005	2.3	80	2	21	59
PA0916-90	133.60	133.96	0.36	0.008	4.4	67	6	40	42
PA0916-91	133.96	134.24	0.28	0.084	29.5	105	93	72	151
PA0916-92	134.24	134.47	0.23	0.110	392.0	193	475	316	530
PA0916-93	134.47	134.80	0.33	0.056	23.2	68	38	45	64
PA0916-94	134.80	135.50	0.70	0.030	8.9	79	10	17	61

DDH - PA-09-17

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA0917-72	110.13	110.63	0.5	<0.005	1.4	89	<2	22	87
PA0917-73	110.63	110.92	0.29	0.136	99.6	45	89	133	319
PA0917-74	110.92	111.09	0.17	0.028	42.9	42	16	39	46
PA0917-75	111.09	111.44	0.35	0.072	14.0	70	12	49	42
PA0917-76	111.44	112.00	0.56	<0.005	<0.5	64	<2	<5	51

DDH - PA-09-18									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-09-18-16	29.22	29.53	0.31	0.060	7.9	86	8	23	87
PA-09-18-22	34.78	35.6	0.82	0.041	3.2	40	<2	29	30
PA-09-18-23	35.6	36.35	0.75	0.015	1.5	64	<2	11	48
PA-09-18-24	36.35	36.94	0.59	<0.005	<0.5	64	<2	8	38
PA-09-18-27	39.05	39.25	0.20	0.008	1.2	49	<2	7	43
PA-09-18-28	39.25	39.89	0.64	0.009	1.5	51	4	14	72
PA-09-18-82	125.50	126.15	0.65	<0.005	1.1	89	<2	11	71
PA-09-18-83	126.15	126.55	0.40	0.023	6.7	92	126	49	466
PA-09-18-84	126.55	126.98	0.43	<0.005	8.6	140	2	17	89
PA-09-18-85	126.98	127.55	0.57	<0.005	6.9	148	3	10	87
PA-09-18-86	127.55	128.00	0.45	<0.005	<0.5	9	15	<5	24
PA-09-18-87	128.00	128.30	0.30	0.009	11.9	196	173	23	677
PA-09-18-88	128.30	128.70	0.40	<0.005	1.8	65	<2	7	55
PA-09-18-98	141.15	141.39	0.24	0.014	1.3	35	6	10	30
PA-09-18-105	152.08	152.81	0.73	0.006	2.2	60	<2	28	44
PA-09-18-106	152.81	153.81	1.00	0.017	2.6	53	<2	25	53
PA-09-18-107	153.81	154.11	0.30	0.089	8.4	37	11	105	48
PA-09-18-108	154.11	154.43	0.32	0.142	12.2	126	9	108	53
PA-09-18-109	154.43	154.86	0.43	0.099	19.2	116	6	87	44
PA-09-18-110	154.86	155.16	0.30	0.239	14.8	53	11	142	43
PA-09-18-111	155.16	155.49	0.33	0.047	8.8	39	16	65	170
PA-09-18-112	155.49	156.00	0.51	0.049	11.1	88	48	63	253
PA-09-18-113	156.00	157.44	1.44	0.009	3.7	72	6	24	61
PA-09-18-114	157.44	157.64	0.20	0.265	14.3	74	28	99	257
PA-09-18-131	173.76	174.81	1.05	<0.005	0.9	87	<2	10	53
PA-09-18-132	174.81	175.75	0.94	<0.005	1.0	66	<2	19	44
PA-09-18-133	175.75	176.33	0.58	<0.005	1.1	63	2	15	55
PA-09-18-134	176.33	177.36	1.03	<0.005	0.8	82	3	18	66
PA-09-18-135	177.36	177.87	0.51	0.013	2.0	73	9	79	41
PA-09-18-136	177.87	178.94	1.07	0.015	2.5	71	14	100	61
PA-09-18-137	178.94	179.57	0.63	0.031	3.8	66	7	35	41
PA-09-18-138	179.57	180.48	0.91	0.028	5.2	78	4	42	35
PA-09-18-139	180.48	181.23	0.75	0.039	8.6	78	11	89	54
PA-09-18-140	181.23	181.80	0.57	0.040	4.9	68	4	40	34
PA-09-18-141	181.80	182.50	0.70	0.086	6.9	17	5	52	26
PA-09-18-142	182.50	183.30	0.80	0.091	3.0	19	2	41	6

DDH - PA-09-18 (continued)									
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-09-18-143	183.30	183.82	0.52	0.115	16.7	47	11	83	42
PA-09-18-144	183.82	184.20	0.38	0.159	17.1	466	85	93	188
PA-09-18-145	184.20	184.89	0.69	0.098	26.0	108	17	124	78
PA-09-18-146	184.89	185.38	0.49	0.127	33.5	78	12	116	41
PA-09-18-147	185.38	186.30	0.92	0.073	38.4	67	10	83	39
PA-09-18-148	186.30	187.00	0.70	0.137	27.7	67	8	112	31
PA-09-18-149	187.00	187.29	0.29	0.155	10.2	19	7	86	7
PA-09-18-150	187.29	188.02	0.73	0.213	16.9	28	7	101	13
PA-09-18-151	188.02	188.40	0.38	1.385	7.3	24	9	348	66
PA-09-18-152	188.40	189.35	0.95	0.283	9.2	425	100	188	164
PA-09-18-153	189.35	190.24	0.89	0.025	3.8	54	22	43	49
PA-09-18-154	190.24	190.87	0.63	0.313	3.5	27	18	96	96
PA-09-18-155	190.87	191.68	0.81	0.019	2.3	49	11	50	60
PA-09-18-156	191.68	192.25	0.57	0.016	2.7	19	5	31	151
PA-09-18-157	192.25	192.65	0.40	0.109	12.7	42	6	99	74
PA-09-18-158	192.65	192.87	0.22	0.042	8.2	21	5	46	60
PA-09-18-159	192.87	193.07	0.20	0.085	10.4	11	17	65	41
PA-09-18-160	193.07	193.57	0.50	0.066	7.9	20	21	44	311

DDH - PA-09-19

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-19-040	49.26	50.02	0.76	0.005	10.6	115	59	12	78	99
PA-10-19-049	58.70	59.70	1.00	0.010	2.0	341	41	3	25	123
PA-10-19-050	59.70	60.00	0.30	0.052	1.7	1920	<1	<2	40	4
PA-10-19-051	60.00	60.37	0.37	0.269	10.0	>10000	14	4	180	10
PA-10-19-052	60.37	60.96	0.59	0.051	3.6	1970	35	<2	55	27
PA-10-19-053	60.96	61.66	0.70	0.223	7.2	>10000	21	<2	200	15
PA-10-19-054	61.66	62.04	0.38	0.101	0.9	4780	<1	3	73	6
PA-10-19-055	62.04	62.49	0.45	0.043	2.7	1400	7	3	57	12
PA-10-19-056	62.49	63.37	0.88	0.010	2.8	502	34	3	74	26
PA-10-19-057		63.83	63.83	<0.005	<0.5	47	54	<2	22	62
PA-10-19-140	183.79	184.27	0.48	0.005	1.6	185	83	<2	24	65
PA-10-19-141	184.27	184.86	0.59	0.022	2.3	539	34	<2	36	53
PA-10-19-142	184.86	185.56	0.70	<0.005	1.3	234	78	<2	69	95
PA-10-19-143	185.56	186.06	0.50	<0.005	1.1	206	34	<2	66	43
PA-10-19-144	186.06	186.91	0.85	<0.005	2.2	96	68	<2	29	74
PA-10-19-145	186.91	187.36	0.45	0.055	8.8	3620	57	11	70	83
PA-10-19-146	187.36	187.77	0.41	0.057	10.6	3190	75	2	85	45
PA-10-19-147	187.77	188.17	0.40	0.018	4.8	481	79	4	82	116
PA-10-19-148	188.17	188.65	0.48	0.005	3.0	114	37	7	64	191
PA-10-19-149	188.65	189.43	0.78	0.007	2.0	168	40	9	44	206
PA-10-19-150	189.43	190.16	0.73	0.088	10.1	1620	32	10	52	203
PA-10-19-151	190.16	190.66	0.50	0.178	7.3	2430	15	4	49	111
PA-10-19-152	190.66	191.05	0.39	0.177	7.0	1850	23	12	48	153
PA-10-19-153	191.05	191.77	0.72	0.068	4.3	1030	20	5	27	69
PA-10-19-154	191.77	192.19	0.42	<0.005	<0.5	22	6	4	12	54
PA-10-19-155	192.19	192.66	0.47	<0.005	<0.5	47	29	7	15	153
PA-10-19-211	289.00	289.50	0.50	<0.005	1.0	11	132	7	<5	129
PA-10-19-212	289.50	290.00	0.50	<0.005	<0.5	5	30	4	<5	100
PA-10-19-213	290.00	290.50	0.50	<0.005	0.6	5	41	8	<5	146
PA-10-19-214	290.50	291.00	0.50	<0.005	0.6	9	35	7	<5	128
PA-10-19-215	291.00	291.85	0.85	<0.005	0.6	5	39	5	<5	134

DDH - PA-09-20

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-20-038	58.87	59.09	0.22	0.323	595.0	4770	44	49	296	375
PA-10-20-039	59.09	59.33	0.24	<0.005	2.1	83	3	5	9	93
PA-10-20-040	59.33	60.05	0.72	<0.005	1.1	30	5	5	5	75
PA-10-20-053	82.07	82.50	0.43	<0.005	<0.5	60	68	<2	24	49
PA-10-20-054	82.50	82.83	0.33	<0.005	<0.5	59	22	4	24	43
PA-10-20-055	82.83	83.80	0.97	<0.005	<0.5	65	77	3	17	47
PA-10-20-056	83.80	84.40	0.60	<0.005	1.0	134	76	<2	22	48
PA-10-20-057	84.40	84.95	0.55	<0.005	4.6	89	49	10	28	178
PA-10-20-058	84.95	85.37	0.42	0.275	807.0	2890	64	71	348	825
PA-10-20-112	163.00	163.57	0.57	<0.005	5.3	264	79	<2	9	68
PA-10-20-113	163.57	164.42	0.85	0.005	5.3	307	73	<2	9	54
PA-10-20-114	164.42	165.29	0.87	0.097	6.3	4100	93	3	29	57
PA-10-20-115	165.29	165.68	0.39	0.185	1185.0	4730	700	23	995	166
PA-10-20-116	165.68	166.68	1.00	0.192	49.4	8010	78	4	81	59
PA-10-20-117	166.68	167.59	0.91	0.113	10.2	3870	50	<2	84	69
PA-10-20-118	167.59	168.01	0.42	0.271	222.0	4940	186	327	274	1220
PA-10-20-119	168.01	168.51	0.50	0.220	21.4	5690	50	182	72	649
PA-10-20-119 BIS	168.51	168.72	0.21	0.194	377.0	5410	72	29	186	155
PA-10-20-120	168.72	169.17	0.45	0.031	4.8	971	74	679	28	2480
PA-10-20-121	169.17	170.15	0.98	0.009	4.0	520	58	5	27	47
PA-10-20-122	170.15	171.33	1.18	0.016	2.6	573	47	4	23	46
PA-10-20-123	171.33	172.33	1.00	<0.005	1.9	213	58	<2	20	54
PA-10-20-124	172.33	173.18	0.85	0.014	2.2	681	55	<2	16	58
PA-10-20-125	173.18	173.33	0.15	0.033	4.2	1450	71	57	28	88
PA-10-20-126	173.33	173.79	0.46	<0.005	5.6	148	147	173	19	343
PA-10-20-127	173.79	174.17	0.38	0.005	2.9	406	65	6	37	60

DDH - PA-09-20 (continued)										
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-20-132	181.82	182.23	0.41	0.006	5.9	318	143	18	22	194
PA-10-20-134	183.38	184.19	0.81	<0.005	6.1	86	617	167	15	238
PA-10-20-135	184.19	185.00	0.81	0.009	6.3	345	174	52	26	206
PA-10-20-149	203.74	204.25	0.51	0.010	1.8	684	110	40	13	64
PA-10-20-153	207.20	207.51	0.31	0.026	3.7	369	39	16	21	35
PA-10-20-154	207.51	207.96	0.45	0.045	4.6	982	60	6	19	40
PA-10-20-160	214.10	214.42	0.32	0.205	15.1	5120	32	7	100	24
PA-10-20-169	221.10	221.54	0.44	<0.005	0.6	137	26	<2	11	378
PA-10-20-170	221.54	222.06	0.52	<0.005	1.0	204	57	<2	11	71
PA-10-20-171	222.06	222.60	0.54	<0.005	<0.5	80	18	2	7	175
PA-10-20-172	222.60	223.00	0.40	<0.005	<0.5	48	26	4	14	27
PA-10-20-173	223.00	223.40	0.40	<0.005	<0.5	31	14	2	22	30
PA-10-20-174	223.40	224.06	0.66	<0.005	<0.5	164	86	2	341	60
PA-10-20-180	228.05	228.46	0.41	0.010	2.4	975	40	3	41	72

DDH - PA-09-21										
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-21-085	145.20	145.78	0.58	<0.005	2.1	196	71	5	11	53
PA-10-21-086	145.78	146.41	0.63	0.010	23.5	129	70	5	15	195
PA-10-21-087	146.41	147.29	0.88	<0.005	2.0	130	93	<2	13	52
PA-10-21-088	147.29	148.07	0.78	<0.005	2.6	71	83	<2	10	105
PA-10-21-089	148.07	149.21	1.14	0.005	1.9	73	55	7	12	178
PA-10-21-090	149.21	150.10	0.89	0.013	55.0	124	27	15	36	224
PA-10-21-091	150.10	150.61	0.51	0.074	616.0	181	203	76	361	979
PA-10-21-092	150.61	150.93	0.32	0.092	88.9	398	17	2	30	73
PA-10-21-093	150.93	151.55	0.62	0.018	8.2	1220	25	3	16	124
PA-10-21-094	151.55	152.12	0.57	0.006	3.9	503	104	<2	11	80
PA-10-21-095	152.12	152.82	0.70	<0.005	2.5	147	85	8	8	75
PA-10-21-096	152.82	153.36	0.54	<0.005	1.7	176	80	<2	11	62
PA-10-21-103	163.40	164.03	0.63	<0.005	<0.5	50	55	<2	27	24
PA-10-21-104	164.03	164.65	0.62	0.008	<0.5	14	60	3	10	26
PA-10-21-109	171.52	172.00	0.48	0.007	43.5	148	69	<2	23	51
PA-10-21-110	172.00	172.53	0.53	<0.005	1.7	224	85	<2	6	70
PA-10-21-112	173.72	174.09	0.37	0.008	2.8	588	59	3	10	68
PA-10-21-113	174.09	174.33	0.24	0.061	86.1	2720	39	11	47	57

DDH - PA-09-21 (continued)										
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-21-114	174.33	174.62	0.29	0.009	4.2	604	34	5	12	104
PA-10-21-121	185.79	186.04	0.25	<0.005	<0.5	28	37	2	<5	41
PA-10-21-123	187.86	188.22	0.36	0.017	15.1	1275	130	9	39	388
PA-10-21-165	256.54	257.03	0.49	0.018	0.8	1600	63	2	70	67
PA-10-21-166	257.03	257.95	0.92	<0.005	0.6	326	62	<2	13	119
PA-10-21-174	266.33	266.83	0.50	<0.005	1.1	190	44	2	46	110
PA-10-21-175	266.83	267.40	0.57	0.012	1.7	608	53	3	35	78
PA-10-21-196	301.42	301.87	0.45	<0.005	3.5	302	82	4	17	92
PA-10-21-197	301.87	302.25	0.38	0.044	20.3	670	101	144	31	748
PA-10-21-198	302.25	302.50	0.25	0.015	66.6	1365	289	482	34	1210
PA-10-21-199	302.50	302.78	0.28	0.053	92.1	1410	170	124	35	479
PA-10-21-200	302.78	303.37	0.59	0.066	248.0	293	576	807	86	759
PA-10-21-201	303.37	303.57	0.20	0.080	283.0	3240	393	2910	158	1540
PA-10-21-202	303.57	303.77	0.20	0.105	198.0	5490	284	480	151	750
PA-10-21-203	303.77	304.05	0.28	0.031	430.0	700	643	3860	250	5130
PA-10-21-204	304.05	304.25	0.20	0.012	14.7	1000	167	263	29	631
PA-10-21-205	304.25	304.55	0.30	<0.005	3.0	398	69	8	10	76

DDH - PA-09-22										
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-10-22-056	90.55	90.92	0.37	0.010	1.8	228	51	6	8	63
PA-10-22-057	90.92	91.15	0.23	0.045	13.0	1210	77	4	27	63
PA-10-22-058	91.15	91.41	0.26	0.076	142.0	980	130	31	60	81
PA-10-22-059	91.41	91.67	0.26	0.019	1.9	522	23	<2	10	31
PA-10-22-060	91.67	92.58	0.91	0.032	4.9	551	45	13	8	57
PA-10-22-061	92.58	92.90	0.32	0.019	4.9	377	43	15	5	54
PA-10-22-061 Bis	92.90	93.25	0.35	0.018	205.0	301	73	34	78	110
PA-10-22-062	93.25	94.04	0.79	0.031	9.7	458	83	<2	15	30
PA-10-22-066	97.55	97.75	0.20	<0.005	1.1	6	93	<2	<5	59
PA-10-22-067	97.75	98.08	0.33	<0.005	1.6	26	149	4	<5	58
PA-10-22-068	98.08	98.87	0.79	<0.005	0.8	13	62	<2	<5	64
PA-10-22-069	98.87	99.20	0.33	0.015	201.0	95	67	98	100	169
PA-10-22-070	99.20	99.55	0.35	<0.005	<0.5	10	109	<2	<5	73
PA-10-22-079	113.35	114.03	0.68	<0.005	<0.5	21	62	3	<5	49
PA-10-22-082	115.75	116.00	0.25	0.008	0.7	377	22	2	24	36

DDH - PA-09-23										
SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA1023-092	143.25	143.60	0.35	0.005	0.6	264	60	5	6	69
PA1023-093	143.60	144.00	0.40	0.018	3.8	738	63	8	25	70
PA1023-094	144.00	144.50	0.50	0.029	5.1	1190	75	10	15	60
PA1023-095	144.50	144.78	0.28	0.043	8.9	1880	112	7	21	82
PA1023-096	144.78	145.45	0.67	0.011	3.1	396	72	6	5	54
PA1023-097	145.45	145.86	0.41	0.030	4.1	1660	60	8	8	54
PA1023-098	145.86	146.34	0.48	0.030	2.9	1820	52	6	6	47

DDH - PA-09-24

SAMPLE	TO	FROM	LENGTH	Au ppm	Ag ppm	As ppm	Cu ppm	Pb ppm	Sb ppm	Zn ppm
PA-1024-117	140.30	140.92	0.62	0.010	3.1	716	64	97	56	159
PA-1024-118	140.92	141.40	0.48	0.331	71.8	3410	63	15	167	123
PA-1024-119	141.40	142.24	0.84	0.098	35.0	371	9	52	40	32
PA-1024-120	142.24	142.67	0.43	0.223	72.3	2320	58	17	169	76
PA-1024-121	142.67	143.52	0.85	0.281	8.7	9020	65	73	381	624
PA-1024-122	143.52	144.07	0.55	0.494	17.7	>10000	83	281	546	89
PA-1024-123	144.07	144.68	0.61	0.408	8.0	7360	94	7	281	127
PA-1024-124	144.68	145.25	0.57	1.155	17.0	10000	131	129	428	1350
PA-1024-125	145.25	145.68	0.43	1.000	172.0	3430	221	910	326	4290
PA-1024-126	145.68	146.03	0.35	0.630	130.0	2290	292	876	339	3950
PA-1024-127	146.03	146.37	0.34	0.221	76.8	1060	135	362	175	1470
PA-1024-128	146.37	146.75	0.38	0.027	181.0	41	30	185	60	196
PA-1024-129	146.75	147.15	0.40	0.705	178.0	1520	357	1410	170	3960
PA-1024-130	147.15	147.90	0.75	1.025	72.9	5800	192	821	368	4150
PA-1024-131	147.90	148.37	0.47	1.320	89.5	4340	71	228	295	1155
PA-1024-132	148.37	148.83	0.46	1.550	39.2	6230	164	553	341	3970
PA-1024-133	148.83	149.35	0.52	0.861	53.0	2550	151	395	179	1830
PA-1024-134	149.35	149.92	0.57	0.238	221.0	1365	78	219	180	1485
PA-1024-135	149.92	150.51	0.59	0.286	1220.0	752	218	530	495	1535
PA-1024-136	150.51	151.07	0.56	0.056	186.0	129	72	61	71	179
PA-1024-137	151.07	151.62	0.55	0.069	187.0	833	176	84	150	322
PA-1024-138	151.62	152.14	0.52	0.077	169.0	574	61	44	96	96
PA-1024-139	152.14	152.49	0.35	1.275	208.0	>10000	278	968	693	3860
PA-1024-140	152.49	153.10	0.61	0.130	44.5	2710	76	86	148	898
PA-1024-141	153.10	153.63	0.53	2.470	80.8	8160	121	187	370	2690
PA-1024-142	153.63	154.50	0.87	0.061	22.3	594	93	76	59	590
PA-1024-143	154.50	155.50	1.00	<0.005	1.9	47	82	19	6	222
PA-1024-144	155.50	156.66	1.16	<0.005	2.1	640	91	34	72	249
PA-1024-145	156.66	157.05	0.39	0.014	22.7	317	75	26	50	117
PA-1024-146	157.05	158.00	0.95	0.065	82.9	1690	82	122	100	81
PA-1024-147	158.00	159.00	1.00	0.050	21.9	2170	61	6	51	73
PA-1024-148	159.00	159.67	0.67	0.041	24.6	1370	53	77	48	550